

Is there a Phase Transition to the Flux Lattice State?

M.A.Moore

Department of Physics, University of Manchester, M13 9PL, United Kingdom.

(February 6, 2008)

The sharp drops in the resistance and magnetization which are usually attributed to a phase transition from the vortex liquid state to a crystal state are explained instead as a crossover between three and two dimensional behavior, which occurs when the phase coherence length in the liquid becomes comparable to the sample thickness. Estimates of the width of the crossover region and the phase coherence length scales are in agreement with experiment.

PACS numbers: 74.60.Ge, 74.20.De

For some years now it has been widely believed that the vortex liquid state of a type-II superconductor changes on cooling to a flux lattice at a first-order phase transition [1]. Sharp drops have been seen in the magnetization [2–4], entropy [5] and resistance [6] and it is usually assumed that such drops are due to a freezing transition. I shall describe here a simple alternative explanation of these drops, based on the idea that they are caused by a crossover from three-dimensional behavior to two-dimensional behavior when the phase correlation length along the field direction in the vortex liquid, $l_{\parallel}$, becomes comparable to the sample dimensions [7]. Because $l_{\parallel}$ grows very rapidly as the temperature is lowered the crossover region appears narrow enough to masquerade as a first order phase transition. An estimate of its width is given and found to be comparable with the width of the drop in the magnetization [3].

Central to my picture is the idea that at all non-zero temperatures the system is in the vortex liquid state and that it is only finite size effects which produce the semblance of a phase transition. In the thermodynamic limit of an infinitely big system there would be no phase transition, no sharp drops and only a vortex liquid phase. At zero temperature in the ground state there would of course be the usual Abrikosov lattice. The length scale over which there is short-range crystalline order in the vortex liquid, $l_{\perp}$, is expected to increase without limit as the temperature is lowered towards absolute zero.

Essentially the picture being advocated here is that of Refs. [8,9], where it was shown that in both two and three dimensions phase coherence in the vortex crystal state was destroyed by the phase fluctuations associated with the shear modes of the crystal and it was suggested that as a consequence crystalline order might not exist in these dimensions. Since it is not obvious why the loss of phase coherence need necessarily imply the absence of crystalline order this suggestion has (to say the least) not been widely accepted. However, our Monte Carlo simulations in two-dimensions [10–12], done within the lowest Landau level approximation (LLL), found no finite temperature phase transition and demonstrated that the length scale over which phase coherence is lost is $l_{\perp}$,

which diverged in the zero-temperature limit.

Strong support for the idea that the apparent first-order phase transition is just a crossover from three to two-dimensional behavior comes from multi-terminal transport (flux transformer) measurements on untwinned single crystals of YBCO [13] and on thin BSCCO crystals [14]. In these experiments current is injected and removed at two electrodes attached to the top face of the crystal and voltage differences measured between two points lying between the electrodes on the top face, V_{TOP} , and between two points directly below them on the bottom face of the crystal, V_{BOT} . The magnetic field is along the c-axis of the crystal and the thicknesses of the YBCO crystals ranged up to $35 \mu\text{m}$ while the BSCCO crystals were around $1 \mu\text{m}$ thick. For crystals of these thicknesses both voltages became very nearly equal to each other as the temperature was reduced after which both fell sharply to zero. The vanishing of the voltage is usually taken as marking the onset of the freezing transition into the crystalline state. When V_{TOP} and V_{BOT} are equal it means the flux lines are moving without cutting and reconnecting so there must be phase coherence across the crystal. As V_{TOP} and V_{BOT} are becoming equal as the “freezing” transition is approached, then the length scale over which there is phase coherence in the direction of the magnetic field, $l_{\parallel}$, must be growing as the temperature of the vortex liquid is reduced, becoming comparable to the crystal thickness right at the apparent phase transition. Furthermore, measurements of the non-linear current-voltage characteristics on the same crystals give information on the length scale $l_{\perp}$ via the scaling relation $\sigma E = Jf(Jl_{\perp}l_{\parallel}\Phi_0/k_BT)$, where E is the electric field perpendicular to the field, J is the current density in the same direction, σ is the conductivity and Φ_0 is the flux quantum [15]. Preliminary studies indicate that it too is a length of micron magnitude [16]. In the conventional picture of a first-order phase transition it is very hard to understand why long-length scales should be present in the vortex liquid — $l_{\parallel}$ is at least as large as $35 \mu\text{m}$ in YBCO at the freezing transition — and why there should be a coincidence of the freezing transition with the temperature at which this length scale becomes

comparable to the dimensions of the sample. My hypothesis that the “freezing” phenomenon is a crossover induced effect seems much more natural.

We start from the Ginzburg-Landau free energy for a superconductor in a uniform magnetic field $\mathbf{B} = \nabla \times \mathbf{A}$;

$$F[\Psi] = \int d^3\mathbf{r} \left(\alpha(T)|\Psi|^2 + \frac{\beta}{2}|\Psi|^4 + \sum_{\mu} \frac{1}{2m_{\mu}} |(-i\hbar\partial_{\mu} - 2eA_{\mu})\Psi|^2 \right). \quad (1)$$

Here $\alpha(T)$ is a temperature-dependent variable e.g. $\alpha(T) = -\alpha'(1 - T/T_{c0})$, T_{c0} is the mean-field transition temperature, β is the coupling constant and m_{μ} is an effective mass. The masses in the ab plane will be taken equal and denoted by m_{ab} and the mass in the c direction is m_c . To start with we shall neglect the fluctuations in the vector potential $\mathbf{A}$ and restrict the order parameter Ψ to the space spanned by the lowest Landau levels (LLL). Then $\alpha_H \equiv \alpha(T) + e\hbar B/m_{ab} = 0$ defines the mean-field line H_{c2} . The temperature is conveniently and conventionally [17] represented by the dimensionless parameter $\alpha_T \equiv \alpha_H(4\pi\hbar^2/\beta e B k_B T \sqrt{2m_c})^{2/3}$. Low temperature is represented by $\alpha_T \rightarrow -\infty$, high temperature by $\alpha_T \rightarrow \infty$. More conveniently $\alpha_T = (2/Gi)^{1/3}(ht)^{-2/3}(1-t-h)$ where Gi is the Ginzburg number, (about 0.02 for YBCO [1]), t is the reduced temperature T/T_{c0} and $h = B/B_{c2}(0)$ where $B_{c2}(0)$ is the straight line extrapolant of the H_{c2} to zero temperature (about 168 T in YBCO [1]).

The length scale $l_{\parallel}$ is a measure of the phase correlation length along the field direction (and is technically the length scale on which the propagator $\langle \Psi^*(x, y, z)\Psi(x, y, z') \rangle$ decreases as a function of $|z - z'|$). The other important length scale in the problem, $l_{\perp}$, which measures the degree of short-range crystalline order in the vortex liquid can be obtained from the density-density correlation function $\langle |\Psi(x, y, z)|^2 |\Psi(x', y', z)|^2 \rangle_c$. In addition $l_{\perp}$ seems to be equal to an (appropriately defined) phase coherence length scale in the direction perpendicular to the field [12]. It is our contention that these lengths reach infinity as the temperature goes to zero and that as a consequence it is useful to use the techniques of “zero-temperature scaling” [18].

At zero-temperature the ground state order parameter $\Psi_0(x, y)$ which minimises $F[\Psi]$ corresponds to the Abrikosov flux lattice of straight vortex lines arranged in the form of a triangular lattice. Expanding about the minimum by setting $\Psi = \Psi_0 + \delta\Psi[x, y, z]$ one finds [8,19] that the low energy states above the minimum can be described by an effective Hamiltonian

$$H = \frac{1}{2} \int d^3\mathbf{r} \left(\rho_s(\partial\theta/\partial z)^2 + c_{66}l^4(\nabla_{\perp}^2\theta)^2 \right). \quad (2)$$

Here θ is the phase change associated with $\delta\Psi$, ρ_s is the superfluid density ($\rho_s = \tilde{\rho}_s\hbar^2|\alpha_H|/m_c\beta$ in the LLL mean-

field limit, with $\tilde{\rho}_s = 1/\beta_A$ and $\beta_A = 1.1596\dots$) and c_{66} is the shear modulus equal in LLL mean-field approximation to $2\tilde{c}_{66}\alpha_H^2/\beta$ with $\tilde{c}_{66} = 0.0885\dots$. The magnetic length scale $l = \sqrt{\hbar/2eB}$. The relation between the phase change θ and flux line displacements is $u_x = -l^2\partial\theta/\partial y$ and $u_y = l^2\partial\theta/\partial x$ [8]. I believe that vortex crystals behave differently from other crystals because only for them can displacements be written as phase derivatives.

It is convenient to introduce the dimensionless variables Z where $z = \xi_c Z$; $\xi_c \equiv (\hbar^2/2m_c|\alpha_H|)^{1/2}$ and $\mathbf{R} = (X, Y)$ where $x = lX$, $y = lY$. Then the effective Hamiltonian in d dimensions becomes

$$\frac{H}{k_B T} = \frac{1}{2\tilde{T}} \int d^2\mathbf{R} \int d^{d-2}\mathbf{Z} \left(\tilde{\rho}_s(\partial\theta/\partial Z_i)^2 + \tilde{c}_{66}(\tilde{\nabla}_{\perp}^2\theta)^2 \right) \quad (3)$$

The subscript i takes values $3, 4, \dots, d$ and an implied summation convention is being used. In three dimensions the dimensionless effective temperature $\tilde{T}$ equals $4\pi/|\alpha_T|^{3/2}$.

For the case of a thin film of thickness L_z where the variation of Ψ with respect to z can be ignored, the Hamiltonian reduces to

$$\frac{H}{k_B T} = \frac{1}{2\tilde{T}} \int d^2\mathbf{R} \tilde{c}_{66}(\tilde{\nabla}_{\perp}^2\theta)^2, \quad (4)$$

where in two dimensions the effective temperature $\tilde{T}$ equals π/α_{2T}^2 , with $\alpha_{2T} = \alpha_H(\pi\hbar L_z/\beta e B k_B T)^{1/2}$.

Hamiltonians such as Eq. (3) have been studied in connection with smectic liquid crystals [20] where a renormalisation group treatment has proved very useful. To this end rescale lengths so that $x' = bx$, $y' = by$ but $z' = b^2z$ when in order to keep the free energy invariant the renormalised temperature $\tilde{T}' = b^{6-2d}\tilde{T}$. Setting $b = e^{\rho}$ one obtains the following flow equation for the effective temperature as a function of the length scale:

$$\frac{d\tilde{T}}{d\rho} = (6 - 2d)\tilde{T}. \quad (5)$$

For dimensions $d \leq 3$ the flow takes one away from low temperatures to the high-temperature sink. Above three dimensions $\tilde{T} = 0$ is a stable fixed point indicating that 3 is the lower critical dimension for behavior controlled by this fixed point.

Consider first the case of thin films ($d = 2$). Starting at a low effective temperature $\tilde{T}$ where the correlation length is $l_{\perp}$, scale up until the effective temperature $\tilde{T}'$ is a , of order unity, and where the correlation length is l . Then $b = l_{\perp}/l$ and $a = \tilde{T}' = (l_{\perp}/l)^2\tilde{T}$ so $l_{\perp} \sim l(1/\tilde{T})^{1/2} \sim l|\alpha_{2T}|$. This result for $l_{\perp}$ is consistent with our Monte Carlo simulations in two dimensions [10–12] and has also been derived within the so-called parquet graph approximation [21]. There have

been a number of other Monte Carlo simulations in two-dimensions employing (the experimentally unrealisable) quasi-periodic boundary conditions and the LLL approximation in which a first order transition to a crystalline state seems to take place at a finite temperature [22]. As no first-order transition has been reported for superconducting films, I shall take the apparent phase transition to be an artifact of the simulations. For a review of this controversy, see Ref. [12].

In thin superconducting films ac resistivities [23] and flux liquid viscosities [24] have been apparently successfully interpreted in terms of the continuous phase transitions predicted in conventional two-dimensional melting theory [25], which would seem to be at odds with the idea that the vortex liquid state should be the only state present at all finite temperatures. These experiments essentially determine the relaxational timescale of the system which grows rapidly at low temperatures. According to our Monte Carlo simulations [11,26] it increases with an Arrhenius form in the two-dimensional effective temperature, i.e. as $\exp(C/\tilde{T})$, with C a constant of order one. Such an expression provides an adequate fit to the experimental data. Invoking a finite temperature phase transition thus seems unnecessary.

Returning now to bulk systems one sees that the term on the right-hand side of Eq. (5) is zero when $d = 3$. To describe three dimensions it is necessary to go beyond the simple scaling flow equation. At low temperatures one expects it to become instead [27], $d\tilde{T}/d\rho = \tilde{T}^2/(2\pi A)$ where A is a constant. On integrating up to the lengthscales at which $\tilde{T}'$ is of order unity, where $b = l_\perp/l = (l_\parallel/\xi_c)^{1/2}$, one has $l_\parallel \sim \xi_c \exp(A|\alpha_T|^{3/2})$ and $l_\perp \sim l \exp(A|\alpha_T|^{3/2}/2)$. Such exponentially rapid growth of correlation lengths is typical of a system at its lower critical dimension. It is perhaps noteworthy that phase coherence length scales of this form were previously obtained via estimates of the crossing energy of flux lines [28].

When the sample thickness L_z is greater than $l_\parallel$ then the system behaves as a three-dimensional bulk system, but as the temperature is lowered $l_\parallel$ grows and eventually becomes greater than L_z . Then the vortices behave as in a two-dimensional thin-film system with phase coherence across the sample. The crossover region is where $L_z \sim l_\parallel$. If one knew A one could get a good estimate of α_T^* , the value of α_T at the crossover, for a sample of known thickness. At this time we shall take α_T^* from experiment [29]. It is around -9 for YBCO crystals of (say) $40 \mu\text{m}$ dimensions [30]. It follows from the definition of α_T that the crossover line obeys the LLL scaling relation $B \sim (T_{c0} - T)^{3/2}$ for fixed L_z , except for temperatures so close to T_{c0} that it is no longer possible to regard ξ_c as a constant.

Because of the exponentially rapid growth of $l_\parallel$, the width of the crossover region as a function of field and

temperature is quite narrow. Its width may be estimated by finding the small change $\delta\alpha_T$ in α_T^* to make $l_\parallel$ grow to $2L_z$. Then $3\delta\alpha_T/2\alpha_T^* \sim \ln(2)/\ln(L_z/\xi_c) \sim \delta B/B$, where δB is the change in B required to double $l_\parallel$. For the 0.2 mm thick crystal of Welp *et al.* [3], we predict that $\delta B/B$ is about 0.054 at a field of 4.2 T while the observed width looks to me to be around 0.2 T , making the ratio $\delta B/B$ about 0.05 . Thus the crossover width is similar to the rounding of the jump in the magnetization. If one believed in a first-order transition one would have to claim that the rounding of the jump was somehow caused by a spatial inhomogeneity of oxygen concentration or some non-uniformity of the applied field. Another feature of our crossover argument is that as the sample thickness is increased then the crossover should occur at lower temperatures, but the decrease of the “transition” temperature is only as the logarithm of the sample thickness. The magnitude of the effect is easily found from solving $L_z \sim l_\parallel$ and certainly looks measurable provided that a range of crystals can be made of various thicknesses but otherwise identical.

When the crossover takes place the effective temperature of the resulting two-dimensional (thin film) state is very low. Using the definition of α_{2T} to re-express it in terms of h and t as $\alpha_{2T} = 0.5(Gi/2)^{1/12}(ht)^{1/6}\alpha_T(L_z/\xi_0)^{1/2}$, where ξ_0 is the zero-temperature c-axis correlation length, $(\hbar^2/2m_c a')^{1/2}$ (which is about $2 \text{ \AA}$) and then inserting numbers appropriate to YBCO at a field of 4 T and sample thickness 0.2 mm one finds $\alpha_{2T} \sim -1600$. Notice that in the crossover region and below, $l_\perp$ is more than $10^3 l$. It would then only require a tiny amount of coupling between the vortex system and the underlying real crystal to produce a system whose structure factor displayed Bragg spots rather than the rings expected for a liquid state [31]. Thus the vortex system would appear crystalline to most experimental probes.

Because the two-dimensional state below the crossover is at such a low effective temperature, its entropy can be obtained by differentiating the mean-field free-energy per unit volume, $-\alpha_H^2/2\beta\beta_A$, with respect to the temperature. However, the entropy of the three-dimensional state when $\alpha_T = \alpha_T^* \sim -9$ is a few percent above the mean-field value [32]. Therefore the entropy must decrease rapidly on cooling through the crossover region, giving rise to an apparent jump. Per vortex per double layer the entropy change ΔS can be written as

$$\Delta S \sim k_B(s/\xi_0)(2/Gi)^{1/6}t^{2/3}h^{-1/3}g(\alpha_T), \quad (6)$$

where h, t and α_T are at their crossover values, s is the distance between the double layers and the function $g(\alpha_T)$ has at present to be inferred from the numerical simulations [32] of specific heats. I estimate that ΔS is around k_B at 4 T . Notice that Eq. (6) predicts that ΔS increases as the field is reduced in accord with experiment [2,4].

The argument of this paper is that the properties of the vortex liquid are controlled by a particular zero-temperature fixed point. Because in dimensions two and three there are diverging length scales associated with this fixed point, the concept of renormalisation group relevance and irrelevance can be used to determine the importance of effects ignored in the calculation. Thus higher Landau levels are clearly irrelevant in the low-temperature limit as they are associated with more massive fields. Similarly screening effects — the fluctuations of the vector potential $\mathbf{A}$ — can be shown to be irrelevant at this zero-temperature fixed point by an extension of the argument used in Ref. [33], where such fluctuations were shown to be also irrelevant at the critical fixed point. Thus our treatment of the length scales $l_{\parallel}$ and $l_{\perp}$ should become exact in the low-temperature limit. However, if there are terms present which couple the vortices to the underlying crystal (as in numerical simulations done on a grid) then a spectrum of low-energy excitations may arise different from that in Eq. (2) which could result in a finite temperature phase transition.

One important effect so far neglected is disorder. After electron irradiation, which induces point defects, the “drops” in the resistance are replaced by a smooth decrease with temperature [34]. Disorder might be expected to limit the growth of $l_{\perp}$ and $l_{\parallel}$ at the Larkin length scales $R_{\perp}$ and $R_{\parallel}$ [1], which would naturally prevent a sharp crossover effect from occurring. Even in non-irradiated samples the resistance drop is much narrower as a function of temperature than the drop in the magnetization. I believe that the sharper drop in the resistance is a consequence of a percolative mechanism in which regions of transverse dimensions $l_{\perp}$ and longitudinal size $l_{\parallel}$ become pinned by the disorder and when these pinned regions percolate across the system then the resistance falls away. In thicker (90 μm) untwinned crystals of YBCO V_{TOP} does not equal V_{BOT} when the resistance drops to zero [35] — a fact consistent with a percolative mechanism.

Thus it seems possible to give an account of the main features of the mixed phase at a semi-quantitative level by employing the ideas of zero-temperature scaling. Should there actually be a finite temperature phase transition then these arguments become irrelevant. However, it is hard to see how the long length scales revealed by the flux transformer experiments can be incorporated into the conventional melting picture.

[1] G. Blatter *et al.*, Rev. Mod. Phys. **66**, 1125 (1994).

- [2] E. Zeldov *et al.*, Nature (London) **375**, 373 (1995).
- [3] U. Welp *et al.*, Phys. Rev. Lett. **76**, 4809 (1996).
- [4] R. Liang *et al.*, Phys. Rev. Lett. **76**, 835 (1996).
- [5] A. Schilling *et al.* (to be published).
- [6] H. Safar *et al.*, Phys. Rev. Lett. **69**, 824 (1992).
- [7] This crossover should not be confused with the “dimensional” crossover which takes place if the flux lines decompose into pancakes [1].
- [8] M. A. Moore, Phys. Rev. B **39**, 136 (1989).
- [9] M. A. Moore, Phys. Rev. B **45**, 7336 (1992).
- [10] J. A. O’Neill and M. A. Moore, Phys. Rev. B **48**, 374 (1993); Phys. Rev. Lett. **69**, 2588 (1992).
- [11] H. H. Lee and M. A. Moore, Phys. Rev. B **49**, 9240 (1994).
- [12] M. Dodgson and M. A. Moore, submitted to Phys. Rev. B.
- [13] D. López *et al.*, Phys. Rev. Lett. **76**, 4034 (1996).
- [14] C. D. Keener *et al.* Ohio State preprint.
- [15] D. S. Fisher, M. P. A. Fisher and D. Huse, Phys. Rev. B **43**, 130 (1991).
- [16] E. F. Righi *et al.*, private communication.
- [17] G. J. Ruggeri and D. J. Thouless, J. Phys. F **6**, 2063 (1976).
- [18] A. J. Bray and M. A. Moore in *Heidelberg Colloquium on Glassy Dynamics*, edited by J. L. van Hemmen and I. Morgenstern (Springer-Verlag, 1987), p121.
- [19] G. Eilenberger, Phys. Rev. **164**, 628 (1967), K. Maki and H. Takayama, Prog. Theor. Phys. **46**, 1651 (1971).
- [20] G. Grinstein and R. A. Pelcovits, Phys. Rev. Lett. **47**, 856 (1981).
- [21] J. Yeo and M. A. Moore, Phys. Rev. Lett. **76**, 1142 (1996); Phys. Rev. B (in press).
- [22] Z. Tešanović and L. Xing, Phys. Rev. Lett. **67**, 2729 (1991). Y. Kato and N. Nagaosa, Phys. Rev. B **47**, 2932 (1993), J. Hu and A. H. MacDonald, Phys. Rev. Lett. **71**, 432 (1993), R. Šásik and D. Stroud, Phys. Rev. B **49**, 16074 (1994).
- [23] P. Berghuis and P. H. Kes, Phys. Rev. B **47**, 262 (1993); A. Yazdani *et al.*, Phys. Rev. Lett. **70**, 505 (1993).
- [24] M. H. Theunissen *et al.*, Phys. Rev. Lett. **77**, 159 (1996).
- [25] D. R. Nelson, in *Phase Transitions and Critical Phenomena*, edited by C. Domb and J. L. Lebowitz (Academic Press, New York, 1983), Vol. 7, p. 5.
- [26] A. K. Kienappel and M. A. Moore (in preparation).
- [27] D. S. Fisher and D. R. Nelson, Phys. Rev. B **16**, 2300 (1977).
- [28] N. K. Wilkin and M. A. Moore, Phys. Rev. B **50**, 10294 (1994).
- [29] Calculations of the value of A are underway; S-K Chin and M.A. Moore, in preparation.
- [30] N. K. Wilkin and M. A. Moore, Phys. Rev. B **48**, 3464 (1993).
- [31] J. Yeo and M. A. Moore, in preparation.
- [32] R. Šásik and D. Stroud, Phys. Rev. Lett. **75**, 2582 (1995).
- [33] E. Brézín, D. R. Nelson and A. Thiaville, Phys. Rev. B **31**, 7124 (1985).
- [34] J. A. Fendrich *et al.*, Phys. Rev. Lett. **74**, 1210 (1995).
- [35] D. López *et al.*, private communication.